

Lexan* 9600 Sheet

Product Datasheet

Description

Lexan* 9600 sheet offers all the benefits of standard, transparent polycarbonate sheet - excellent impact resistance, good stiffness and strength, high optical quality, excellent formability, relatively light weight - but it has significantly better flammability characteristics, making it suitable for a wide variety of applications in the transportation, electrical and electronic industries.

Typical Property Values ♦

Property	Test Method	Unit	Value
Physical			
Density	ISO 1183	g/cm ³	1.20
Water absorption, equilibrium, 23°C	ISO 62	%	0.35
Rockwell Hardness	ASTM D785		M74
Mechanical			
Tensile Strength, yield	ISO 527	MPa	60
Tensile Strength, break	ISO 527	MPa	70
Tensile modulus	ISO 527	MPa	2350
Tensile elongation, break	ISO 527	%	120
Flexural strength, yield	ISO 178	MPa	90
Flexural modulus	ISO 178	MPa	2300
Izod notched impact, 23°C	ISO 180/1A	kJ/m ²	65
Gardner impact, 23°C	ASTM D3029	J	>40
-30°C		J	>40
Taber Abrasion, CS17, 1000g, 1000cycles	ASTM D1242	mg	9
Thermal			
Vicat Softening Temp, Rate B /120	ISO 306	°C	145
DTUL, 0.45 MPa	ISO 75/Be	°C	138
Thermal Conductivity	ASTM C 177	W/m°C	0.20
Mold Shrinkage	ISO 527	%	0.6-0.8
Coefficient of Thermal Expansion	ASTM D696	1/°C	7×10 ⁻⁵
Electrical			
Dielectric Strength	IEC 60243	kV/mm	17
Dielectric Constant, 60Hz			3.17
1 MHz			2.96
Dissipation Factor 50Hz	ASTM D150		0.001
	1MHz		0.01
Volume Resistivity, 23°C	IEC 60093	Ohm.cm	>10 ¹⁵

♦ These property values have been derived from zc* resin data for the material used to produce this sheet product.
* Lexan is a trademark of General Electric Company



Lexan* 9600 Sheet

Product Datasheet

Processing

Lexan* 9600 sheet is ideally suited to thermoforming. It offers high, deep draw ratios, equal wall thickness distribution, and it can be formed into complex shapes using standard thermoforming equipment. Sandwich type heating systems give the best results. Lexan 9600 sheet has a forming temperature range of 185 - 205°C. When forming, a draft angle of at least 3° should be allowed and post mold shrinkage of 0.6 - 0.8% taken into account.

Pre-drying

It is important to ensure that Lexan 9600 sheets are free of moisture prior to thermoforming. A hot air circulating oven set at 120°C is recommended. Pre-drying times vary from 3-24 hours, depending on sheet thickness.

Assembling

Parts made from Lexan 9600 sheet can be assembled with plastics, metals, rubber and other materials using many types of adhesive bonding, welding and mechanical fastening techniques. Since some of these materials can cause environmental stress cracking, please consult GE-Plastics, Specialty Film & Sheet for advice on specific applications.

Painting

Lexan 9600 sheet is ideally suited for use with a wide variety of modern decoration techniques. A list of approved paint systems and suppliers is available upon request.

Chemical resistance

Lexan 9600 sheet has sufficient resistance to most mineral oils, greases, aliphatic hydrocarbons and acids under low or moderate stress levels. In applications where the Lexan 9600 sheet will come into contact with aggressive chemicals, specific (application related) testing is always advised. Effective painting systems can improve chemical resistance.

Fire test performance

Lexan 9600 sheet has good fire performance against many national fire codes dependent on thickness and color; please check with the local sales office for details.

Americas:

GE
Plastics
Specialty Film & Sheet
One Plastics Avenue
Pittsfield, MA 01201
USA
Tel. (1) (413) 448 7110
Fax. (1) (413) 448 7506

Europe:

GE
Plastics
Specialty Film & Sheet
Plasticslaan 1
4612 PX Bergen op Zoom
The Netherlands
Tel. (31) (164) 292742
Fax. (31) (164) 293272

Pacific:

GE
Plastics
Specialty Film & Sheet
1468 Nanjin Road (W)
26th Floor, United Plaza
200040 Shanghai China
Tel. (86) 21 3222 4500
Fax. (86) 21 6289 8998

For more information call:

(800) 451-3147

Visit us online at:
www.geplastics.com

©2005 General Electric Company
All Rights Reserved

DISCLAIMER: THE MATERIALS, PRODUCTS AND SERVICES OF THE BUSINESSES MAKING UP THE PLASTICS BUSINESS UNIT OF GENERAL ELECTRIC COMPANY, ITS SUBSIDIARIES AND AFFILIATES, ARE SOLD SUBJECT TO ITS STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, GE'S PLASTICS BUSINESS MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING ITS PRODUCTS, MATERIALS, SERVICES, RECOMMENDATIONS OR ADVICE. EXCEPT AS PROVIDED IN GE'S PLASTICS BUSINESS' STANDARD CONDITIONS OF SALE, GE'S PLASTICS BUSINESS AND ITS REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS OR SERVICES DESCRIBED HEREIN. Each user bears full responsibility for making its own determination as to the suitability of GE's Plastics business' products, materials, services, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating GE's Plastics business' products, materials, or services will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of GE's Plastics business' Standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by GE's Plastics business. No statement contained herein concerning a possible or suggested use of any material, product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of General Electric Company or any of its subsidiaries or affiliates covering such use or design, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.

* Trademark of General Electric Company

